

# PC 150 WHITE PRIMER

## PRECAT PRIMER

### DESCRIPTION

PC 150 White Primer is a fast drying, high solids, pre-catalyzed primer designed for interior wood products. This primer has excellent filling, hiding and sanding characteristics making it an excellent choice for millwork. PC 150 White Primer should be topcoated with recommended LORCHEM pigmented pre-catalyzed lacquers. The PC 150 primer is available in a black primer and neutral base.

### PRODUCT DATA

|                                    |          |                                 |                               |                     |
|------------------------------------|----------|---------------------------------|-------------------------------|---------------------|
| <b>Color</b>                       | White    | <b>VOC less exempts</b>         | 556.11 g/L                    | 4.64 lb/gal0        |
| <b>Solids % by Vol</b>             | 30% ± 2% | <b>VOC actual</b>               | 559.20 g/L                    | 4.67lb/gal          |
| <b>Solids %by Wt</b>               | 49% ± 2% | <b>Photochemical reactive</b>   | No                            |                     |
| <b>Density</b>                     | 1.23     | <b>Flash Point (PM/CC)</b>      | N/A                           |                     |
| <b>Viscosity 23°C/73°F #4 Ford</b> | 94± 2%   | <b>Shelf life</b>               | 6 months (at 15-25°C/59-77°F) |                     |
| <b>Gloss( On Black glass @60°)</b> | Flat     | <b>Theo-coverage @1 mil dry</b> | 359 Sq.Ft/gal                 | 9 m <sup>2</sup> /L |

### PREPARATION/APPLICATION

|                            |   |
|----------------------------|---|
| <b>Working Temp</b>        | >18°C/65°F surface, coating and air   |
| <b>Catalyzation</b>        | N/A   |
| <b>Pot life</b>            | N/A   |
| <b>Reducer</b>             | Reduce 10-15% by volume with Thinner DX 180 (Medium), Thinner DX 195 (slow).  |
| <b>Film thickness</b>      | Min 4 mil wet – 5 mil wet   |
| <b>Suggested Topcoat</b>   | UNILAC 100 WHITE, POLYACRIL 99 WHITE  |
| <b>Application</b>         | <ul style="list-style-type: none"> <li>Apply a full coat of PC 150 WHITE PRIMER at 4.0 – 5.0 wet mils.</li> <li>Allow to dry. Sand with 240, 320 paper, or sponges as required. A second coat of primer surfacer may be applied after sanding if needed for additional filling. Sand again before topcoating. Topcoat within 8 hours of sanding</li> <li>Topcoat – apply recommended topcoat at 4.0 - 5.0 mils wet</li> <li>Do not exceed 6.0 mils DFT for the total system.</li> </ul> |
| <b>Surface Preparation</b> | Wood surface must be clean, dry, free of grease and oil and finish sanded with 180 grit sandpaper to ensure optimum adhesion and coating performance properties. Moisture content of the wood should be between 6%-8%.  |
| <b>Use Directions</b>      | For interior use only. Adjust viscosity and stir thoroughly before application to avoid variations application. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.  |
| <b>App equip.</b>          | Conventional & HVLP Siphon Feed, Pressure Pot Systems and Airless/Air Assist Equipment.   |
| <b>Tinting</b>             | Can be tinted up to 10% maximum with universal colorants 844.   |
| <b>Cleanup</b>             | Clean tools/equipment immediately after use with T750 LORCHEM cleaner gun or a quality lacquer thinner or acetone. Always follow manufacturer’s safety recommendations when using any solvent.  |
| <b>Standards</b>           | This product meets KCMA and CKCA test requirements when used under recommended LORCHEM Topcoat.   |

### DRYING TIMES

| Method     | Drying temperature. | Drying Time (@ 50%RH and thickness @ 4 mil WET) |               |                      |         |
|------------|---------------------|---|---------------|----------------------|---------|
| Air Drying | 23°C/74°F           | <b>Dust free time</b>                           | 4-6 minutes   | <b>Dry to sand</b>   | 1 hour  |
|            |                     | <b>Dry to touch</b>                             | 20-30 minutes | <b>Dry to recoat</b> | 1 hour  |
|            |                     | <b>Dry to Handle</b>                            | 1 hour        | <b>Dry to stack</b>  | 6 hours |
| Force dry  | 45to 60°C/110-140°F | Minutes   |               |                      |         |

**Note:** Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Minimum curing temperatures of 23°C/74°F must be maintained throughout curing cycle to achieve the film integrity as stated in product features.

# PC 150 WHITE PRIMER

## PRECAT PRIMER

### APPLICATION RECOMMENDATIONS

#### APPLICATION EQUIPMENT SETTINGS

| Method of Application | Air Pressure (PSI) | Fluid Pressure (PSI) | TIP size (mm / inch)  | Application Viscosity (#FORD 4) | Thickness Film (Mils) |
|-----------------------|--------------------|----------------------|-----------------------|---------------------------------|-----------------------|
| Conventional spray    | 40-50              | 08-12                | 1.8-2/0,070-0,078     | 18-21                           | 3-5                   |
| Airless Spray         | 10-18              | 300-600              | 0,28-0,33/0,011-0,012 | 18-21                           | 3-5                   |
| HVPL                  | 35-45              | 8-12                 | 1.19-1,39/0,047-0,055 | 18-21                           | 3-5                   |

**Note:** All measurements and application equipment settings are based on application at a temperature of 23°C/74°F. Viscosity will vary depending on the temperature of the liquid. The above-mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

#### SPECIFICATIONS

- ◆ For interior use only.
- ◆ Must be before and during using.
- ◆ This product should be thoroughly sanded within 4 hours of being applied. If the primer is not topcoated the same day, it should be resanded immediately before topcoating to insure optimum intercoat adhesion.
- ◆ Store at room temperature (under 25°C/ 80° F). Higher temperatures will reduce the shelf life.
- ◆ Can be used under recommended LORCHEM Topcoat. Please contact your LORCHEM representative for system recommendations.
- ◆ Total film thickness of systems must not exceed 7.0 mils dry film because heavier films may show cracking tendency.

### CAUTIONS

#### TESTING

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

#### THESE PRODUCT ARE DESIGNED FOR INDUSTRIAL SHOP APPLICATION AND PROFESSIONAL USE ONLY

Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. Please direct any questions or comments to your local representative.

#### PDS

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling, preparation and application which are not known or under our control, LORCHEM cannot make any warranties related to the product or the performance of the product. Moreover, we underline the fact that in industrial applications, a tolerance of 5% in the overall results is considered normal and is not caused by the quality of the product.

### CONTACT

PH: +1(450)424-4000

F: +1(450) 424-9134

<http://www.lorchemintl.com>

#### LORCHEM INTERNATIONAL

150,Rue Aimé-Vincent Vaudreuil, Dorion,  
QC J7V5V5