

VITROPRIMER 157

MODIFIED VINYL PRIMER



DESCRIPTION

VITROPRIMER 157 is a fast drying and high solids vinyl modified primer. This precatalyzed primer is designed for coating interior wood furniture and other interior wood products. This primer is easy to sand with excellent filling and hiding characteristics. Typical applications include kitchen cabinets, vanities, chairs, office and household furniture.

PRODUCT DATA

Color	White	VOC less exempts	644.25 g/L	5.38 lb/gal
Solids % by Vol	21% ± 2%	VOC actual	598.40 g/L	4.99 lb/gal
Solids %by Wt	36% ± 2%	Photochemical reactive	No	
Density	1.08	Flash Point (PM/CC)	N/A	
Viscosity 23°C/73°F #4 Ford	55 ± 2%	Shelf life	6 months (at 15-25°C/59-77°F)	
Gloss(On Black glass @60°)	Flat	Theo-coverage @1 mil dry	272 Sq.Ft/gal	7 m ² /L

PREPARATION/APPLICATION

Working Temp	>18°C/65°F surface, coating and air
Catalyzation	N/A
Pot life	N/A
Reducer	Product can be applied without reduction. If reduction is needed to adjust drying or build, reduce 15-25% by volume with DX 180 THINNER (Medium), DX 195 THINNER (slow).
Film thickness	Min 4 mil wet – 6 mil wet.
Suggested Topcoat	UNILAC 100 WHITE, POLYACRIL 99 WHITE, AKRYLAK 202 WHITE
Application	<ul style="list-style-type: none"> Apply a full coat of VITROPRIMER 157 at 4.0 – 6.0 wet mils. Allow to dry. Sand with 240, 320 paper. A second coat of primer may be applied after sanding if needed for additional filling. Sand again before topcoating. Topcoat within 8 hours of sanding Topcoat – apply recommended topcoat at 4.0 - 6.0 mils wet
Surface Preparation	Wood surface must be clean, dry, free of grease and oil and finish sanded with 180 grit sandpaper to ensure optimum adhesion and coating performance properties. Moisture content of the wood should be between 6%-8%.
Use Directions	For interior use only. Adjust viscosity and stir thoroughly before application to avoid variations application. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.
App equip.	Conventional & HVLP Siphon Feed, Pressure Pot Systems and Airless/Air Assist Equipment.
Tinting	Can be tinted up to 10% maximum with universal colorants 844.
Cleanup	Clean tools/equipment immediately after use with T750 LORCHEM cleaner gun or a quality lacquer thinner or acetone. Always follow manufacturer's safety recommendations when using any solvent.
Standards	This product meets KCMA and CKCA test requirements when used under recommended LORCHEM Topcoat.

DRYING TIMES

Method	Drying temperature.	Drying Time (@ 50%RH and thickness @ 4 mil WET)			
Air Drying	23°C/74°F	Dust free time	4-6 minutes	Dry to sand	45 minutes
		Dry to touch	20-30 minutes	Dry to recoat	45 minutes
		Dry to Handle	45 minutes	Dry to stack	6 hours
Force dry	45to 60°C/110-140°F	Minutes			

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Minimum curing temperatures of 23°C/74°F must be maintained throughout curing cycle to achieve the film integrity as stated in product features.

VITROPRIMER 157

MODIFIED VINYL PRIMER



APPLICATION RECOMMENDATIONS

APPLICATION EQUIPMENT SETTINGS

Method of Application	Air Pressure (PSI)	Fluid Pressure (PSI)	TIP size (mm / inch)	Application Viscosity (#FORD 4)	Thickness Film (Mils)
Conventional spray	40-50	08-12	1.8-2/0,070-0,078	18-21	3-5
Airless Spray	10-18	300-600	0,28-0,33/0,011-0,012	18-21	3-5
HVLP	35-45	8-12	1.19-1,39/0,047-0,055	18-21	3-5

Note: All measurements and application equipment settings are based on application at a temperature of 23°C/74°F. Viscosity will vary depending on the temperature of the liquid. The above-mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

SPECIFICATIONS

- ◆ For interior use only.
- ◆ Must be agitated before and during using.
- ◆ This product should be thoroughly sanded within 4 hours of being applied. If the primer is not topcoated the same day, it should be resanded immediately before topcoating to insure optimum intercoat adhesion.
- ◆ Store at room temperature (under 25°C/ 80° F). Higher temperatures will reduce the storage life.
- ◆ Can be used under recommended LORCHEM Topcoat. Please contact your LORCHEM representative for system recommendations.
- ◆ Total film thickness of systems must not exceed 7.0 mils dry film because heavier films may show cracking tendency.

CAUTIONS

TESTING

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

THESE PRODUCT ARE DESIGNED FOR INDUSTRIAL SHOP APPLICATION AND PROFESSIONAL USE ONLY

Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. Please direct any questions or comments to your local representative.

PDS

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling, preparation and application which are not known or under our control, LORCHEM cannot make any warranties related to the product or the performance of the product. Moreover, we underline the fact that in industrial applications, a tolerance of 5% in the overall results is considered normal and is not caused by the quality of the product.

CONTACT

PH: +1(450)424-4000

F: +1(450) 424-9134

<http://www.lorchemintl.com>

LORCHEM INTERNATIONAL

150, Rue Aimé-Vincent Vaudreuil, Dorion,
QC J7V5V5